


1K

DIN EN 857 1SC



内胶层：耐油合成橡胶
 增强层：1 层高抗拉钢丝编织
 外胶层：耐天候合成橡胶
 主要应用：安装空间狭小的中低压管，
 回油管（吸气管 DN≤31）

连续作业：-40℃~+100℃ -10°F~+212°F
 最高工作温度：121℃ 250°F
 建议使用流体介质：矿物油、菜油和油菜籽
 油、二醇和聚乙二醇基油、合成酯基油、水 / 乳
 化油

													
HOSE SIZE		R.O.D		O.D		MAX W.P		BURST PRESSURE		MIN. BEND RADIUS		WEIGHT	
DN	inch	mm	inch	mm	inch	bar	psi	bar	psi	mm	inch	g/m	lb/ft
6	1/4"	10.2	0.40	12.0	0.47	225	3260	1050	15220	50	1.97	185	0.12
8	5/16"	11.5	0.45	13.6	0.54	215	3110	1000	14500	55	2.17	215	0.14
10	3/8"	13.6	0.54	15.5	0.61	180	2610	850	12320	60	2.36	265	0.18
12	1/2"	17.1	0.67	18.9	0.74	160	2320	660	9570	70	2.76	335	0.23
16	5/8"	20.6	0.81	22.4	0.88	130	1880	620	8990	90	3.54	445	0.30
19	3/4"	23.9	0.94	25.9	1.02	105	1520	480	6960	100	3.94	540	0.36
25	1"	31.3	1.23	33.3	1.31	88	1270	400	5800	160	6.30	770	0.52
31	1.1/4"	38.4	1.51	40.9	1.61	63	910	400	5800	210	8.27	1080	0.73
38	1.1/2"	45.0	1.77	47.5	1.87	50	720	200	2900	300	11.81	1220	0.82
51	2"	58.0	2.28	60.5	2.38	40	580	160	2320	400	15.75	1630	1.10
63	2.1/2"	70.5	2.78	73.0	2.87	50	720	200	2900	760	29.92	2090	1.40
76	3"	85.0	3.35	87.7	3.45	35	500	140	2030	900	35.43	2780	1.87